

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
1.	BC-10		18.06	2.95	5.01	5.44	7.20	3.02	1.98	4.58	69.28	19.08	1.25	
2.	BC-10		36.6	1.79	3.73	4.19	11.70	8.24	6.18	4.01	69.53	19.95	1.16	
3.	BC-10		33.52	1.74	3.69	4.47	13.44	9.17	7.46	9.56	62.94	20.64	1.09	
4.	BC-10		9.34	2.72	5.51	5.70	7.20	1.68	0.55	5.66	63.99	22.01	1.98	
5.	BC-10		17.42	2.83	4.88	5.61	11.64	6.75	4.98	8.25	66.32	18.92	1.18	
6.	BC-10		19.62	2.43	4.50	4.92	7.28	3.14	1.96	5.02	65.78	22.03	1.36	
7.	BC-10		12.92	2.84	5.42	5.36	8.40	3.39	1.43	5.13	66.13	21.37	1.33	
8.	BC-10		16.46	3.55	5.59	5.62	6.23	1.60	0.77	5.48	64.32	22.61	1.56	
9.	BC-10		32.62	1.97	3.60	3.97	8.58	5.44	4.36	5.32	67.92	18.83	2.10	
10.	BC-10		8.12	3.44	5.38	5.93	7.11	2.44	1.08	5.70	64.53	22.19	1.61	
11.	BC-10		5.5	4.06	6.11	6.17	6.36	1.42	0.40	5.82	64.45	22.23	1.36	
12.	BC-10		16.38	3.07	4.81	5.27	7.54	3.09	2.26	5.59	67.75	20.25	1.05	
13.	BC-10		17.22	3.95	7.11	8.65	10.89	5.19	4.36	6.40	64.59	20.30	3.39	
14.	BC-10		15.48	1.30	3.13	3.47	9.95	6.16	4.77	4.31	69.65	19.43	1.33	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
15.	BC-11		15.48	1.68	3.65	4.71	9.08	4.58	3.04	4.07	68.82	20.68	1.07	
16.	BC-11		14.12	1.58	4.33	4.76	9.33	4.48	3.15	4.23	69.00	20.46	1.03	
17.	BC-11		31.8	1.26	2.82	3.45	9.03	5.22	3.88	4.11	68.14	20.93	1.21	
18.	BC-11		37.36	1.44	3.43	4.04	9.26	5.48	3.97	4.16	69.01	19.14	1.89	
19.	BC-11		24.88	2.19	4.79	5.06	9.05	3.72	2.93	5.01	66.92	20.50	1.68	
20.	BC-11		31	1.63	3.42	5.06	9.39	5.65	4.38	4.11	69.16	19.30	1.52	
21.	BC-11		24.26	2.01	4.06	4.69	8.62	8.10	3.05	4.56	66.66	21.14	1.59	
22.	BC-11		16.7	1.91	4.49	5.19	8.42	3.49	1.91	4.90	66.03	21.26	1.77	
23.	BC-11		30.62	1.18	2.50	3.31	9.32	6.07	4.65	3.36	70.33	19.08	1.15	
24.	BC-11		1.64	4.96	6.96	7.09	5.60	0.37	0.18	6.72	62.73	22.03	1.75	
25.	BC-11		14.42	3.41	5.62	5.69	7.14	2.12	1.77	5.43	65.14	21.99	1.33	
26.	BC-11		6.26	5.08	6.90	6.69	6.50	0.86	0.45	8.34	62.74	21.04	1.55	
27.	BC-11		15.24	2.84	4.87	5.03	6.77	2.88	2.14	4.95	67.11	20.80	1.16	
28.	BC-11		14.84	3.89	5.66	5.68	6.65	1.97	1.51	5.63	65.34	21.69	1.42	
29.	BC-11		18.76	2.61	4.09	4.78	7.78	3.58	2.74	5.11	67.68	20.26	1.26	
30.	BC-11		16.74	1.93	4.30	4.61	8.71	4.01	3.17	4.85	67.15	20.60	1.74	
31.	BC-11		11.3	3.12	5.66	5.95	8.39	3.12	2.31	5.68	67.10	19.88	1.42	
32.	BC-11		12	2.80	5.40	5.57	10.56	4.99	3.87	8.28	65.83	19.65	1.24	
33.	BC-11		22.68	1.48	3.56	4.45	9.31	6.55	4.88	6.74	68.45	18.60	1.12	
34.	BC-11		22.58	1.23	2.95	3.78	8.85	5.60	4.18	5.21	72.03	16.90	1.40	
35.	BC-11		3.42	4.18	7.27	6.49	6.83	0.61	0.73	5.42	63.93	22.89	1.03	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
36.	BC-12		10.5	2.94	6.25	6.37	10.18	3.58	0.18	5.22	65.55	22.45	1.32	
37.	BC-12		32.3	1.58	3.10	5.22	9.45	6.40	5.11	4.72	67.69	20.04	1.98	
38.	BC-12		30.58	1.95	3.87	4.42	11.07	6.64	4.87	3.88	67.76	20.28	1,98	
39.	BC-12		34.18	1.56	3.49	4.06	10.18	7.01	5.05	3.98	67.89	21.16	1.56	
40.	BC-12		26.16	1.82	4.77	5.65	10.86	6.30	4.72	4.14	64.82	23.28	1.65	
41.	BC-12		32.58	1.23	2.75	4.05	9.60	5.37	4.94	4.01	65.90	22.98	1.13	
42.	BC-12		5.18	6.44	8.04	7.97	7.19	1.28	0.15	11.54	59.56	22.58	1.27	
43.	BC-12		4.82	5.70	7.94	7.57	6.57	1.57	0.56	8.26	61.84	23.21	1.30	
44.	BC-12		14.22	2.17	4.65	5.40	9.82	4.81	3.14	6.58	68.65	19.37	1.07	
45.	BC-12		22.92	2.09	5.18	5.67	11.14	6.71	4.22	6.16	63.80	21.31	3.47	
46.	BC-12		18.26	3.56	7.81	7.20	11.07	4.15	2.32	4.53	67.90	19.40	2.04	
47.	BC-12		31.06	1.40	4.31	5.27	11.34	7.14	6.29	3.90	68.16	21.60	0.83	
48.	BC-12		23.72	1.91	4.57	5.70	11.06	5.74	4.20	4.04	68.26	20.48	1.55	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
49.	BC-13		29.1	1.54	3.62	4.17	8.05	4.50	4.35	4.35	70.23	19.25	1.09	
50.	BC-13		12.16	3.68	5.92	6.15	6.04	1.24	0.47	5.63	66.53	20.80	1.31	
51.	BC-13		11.38	3.65	6.10	6.44	7.59	2.85	1.73	5.66	67.64	20.00	1.30	
52.	BC-13		29.62	1.38	3.29	4.03	9.21	6.73	4.58	4.52	67.95	20.85	1.20	
53.	BC-13		29	1.24	3.37	4.43	9.71	5.98	4.43	4.11	68.17	20.87	1.05	
54.	BC-13		25.62	2.36	4.69	4.81	10.11	4.83	3.30	5.84	65.02	20.49	2.99	
55.	BC-13		38.9	1.36	3.82	5.25	10.64	6.02	4.20	4.95	67.45	20.10	1.81	
56.	BC-13		38.94	1.06	3.17	3.88	11.21	7.17	5.39	4.68	65.97	20.72	2.69	
57.	BC-13		20.7	1.77	4.33	5.29	10.27	6.39	5.11	6.57	65.12	20.05	2.46	
58.	BC-13		32.56	0.84	2.96	4.04	12.21	7.86	6.05	4.88	66.23	21.53	1.89	
59.	BC-13		28.7	0.59	2.48	3.55	12.46	9.43	7.21	4.33	70.57	18.95	1.53	
60.	BC-13		14.58	1.79	6.46	5.82	10.88	2.77	1.17	4.4	67.76	19.65	1.75	
61.	BC-13		23.34	1.36	4.49	6.06	12.05	5.74	2.90	4.33	68.74	19.86	1.18	
62.	BC-13		24.72	0.65	4.83	6.20	14.59	8.09	6.38	3.94	69.09	19.66	1.64	
63.	BC-13		26.2	1.30	3.07	3.70	10.01	7.53	4.43	4.9	68.23	18.95	2.24	
64.	BC-13		19.2	0.99	4.33	5.48	11.74	5.33	3.47	4.45	69.40	18.38	2.05	
65.	BC-13		21.58	1.06	4.12	5.32	13.95	7.88	5.20	3.9	69.16	19.92	1.38	
66.	BC-13		40.46	0.63	2.33	3.35	11.73	8.78	6.86	4.73	67.35	20.29	2.27	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
67.	BC-14		17.94	4.35	5.92	5.30	5.31	0.44	0.33	5.93	64.49	21.52	1.97	
68.	BC-14		16.52	1.28	3.63	3.95	9.33	5.10	4.08	4.85	67.68	19.56	1.21	
69.	BC-14		17.96	2.72	5.12	5.24	8.42	3.20	2.42	5.23	66.99	20.07	1.18	
70.	BC-14		12.92	2.74	4.99	4.70	7.41	2.71	2.09	5.17	66.99	20.01	1.23	
71.	BC-14		41.4	0.32	1.74	2.33	11.38	7.34	6.13	3.58	70.67	18.33	0.98	
72.	BC-14		19.2	1.18	3.55	4.40	9.88	5.90	5.29	6.45	65.33	20.85	1.44	
73.	BC-14		9.56	3.04	5.27	5.84	7.03	3.21	1.14	6.22	65.90	20.53	1.31	
74.	BC-14		25.04	2.50	6.40	8.88	12.16	7.69	5.20	5.17	69.29	18.39	1.14	
75.	BC-14		29.2	1.18	3.23	3.77	10.28	6.31	4.61	4.74	67.55	19.64	1.98	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
76.	BC-15		23.4	1.01	2.88	3.63	9.14	5.67	3.97	4.27	70.23	19.04	1.22	
77.	BC-15		21.34	3.24	5.37	5.84	8.19	3.33	2.34	5.24	66.90	19.66	2.68	
78.	BC-15		21.28	1.97	4.28	4.48	8.88	4.16	3.65	4.7	68.95	19.81	1.22	
79.	BC-15		27.46	1.70	3.16	3.79	8.34	5.43	4.33	4.68	66.62	22.20	1.18	
80.	BC-15		24.84	2.18	4.66	4.65	7.70	3.49	2.88	5.02	67.82	19.91	1.31	
81.	BC-15		43.34	0.99	2.39	3.27	9.76	6.73	5.20	3.3	68.97	20.34	1.25	
82.	BC-15		7.74	3.49	6.49	7.46	8.20	1.21	0.40	5.69	64.49	21.89	1.44	
83.	BC-15		24.18	1.70	4.03	4.74	9.05	4.37	2.98	5.57	66.75	20.51	1.49	
84.	BC-15		33.96	1.36	2.80	5.33	8.94	5.92	4.36	4.74	68.44	20.30	1.23	
85.	BC-15		20.7	2.50	4.53	5.40	7.82	3.47	1.93	5.31	65.64	21.18	1.54	
86.	BC-15		9.06	3.53	6.05	6.28	7.74	1.70	0.41	6.86	63.75	21.78	1.52	
87.	BC-15		10.88	3.02	5.39	5.68	7.10	2.24	1.19	5.45	66.55	20.52	1.36	
88.	BC-15		18.16	3.25	5.47	5.55	6.94	2.72	1.53	5.57	66.58	20.52	1.38	
89.	BC-15		19.66	2.60	5.15	5.77	8.20	3.63	2.35	5.05	66.78	20.98	1.29	
90.	BC-15		27.86	1.93	3.48	4.25	8.58	5.48	3.82	4.9	69.09	19.20	1.43	
91.	BC-15		10.7	2.74	4.92	5.47	7.85	3.46	2.49	5.52	66.19	20.97	1.31	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
92.	BC-16		22.04	2.01	4.63	4.93	8.92	4.06	2.42	4.68	69.27	19.42	1.30	
93.	BC-16		23.26	2.22	4.59	4.62	8.09	3.72	2.37	4.47	69.31	19.19	1.20	
94.	BC-16		38.64	1.80	3.71	4.12	8.21	4.84	3.83	4.67	69.14	19.17	1.89	
95.	BC-16		37.84	1.24	2.75	3.38	10.06	5.84	5.53	3.87	69.72	18.79	1.93	
96.	BC-16		41.42	1.18	3.04	3.55	9.60	6.80	5.65	3.98	67.76	20.19	1.97	
97.	BC-16		19.84	1.93	3.80	4.02	8.47	4.70	3.34	4.28	67.58	20.15	1.78	
98.	BC-16		30.5	2.05	4.22	4.30	7.49	3.45	2.73	4.68	66.95	20.69	1.92	
99.	BC-16		22.84	2.19	4.71	5.15	8.40	3.54	2.51	4.75	67.16	20.64	1.25	
100.	BC-16		17.9	2.43	4.70	4.64	7.82	2.29	2.55	5.11	67.38	20.20	1.26	
101.	BC-16		31.18	1.36	3.00	3.63	10.35	6.26	4.81	4.91	70.03	18.56	1.07	
102.	BC-16		16.82	2.11	4.07	4.76	8.22	4.17	2.88	5.36	67.37	20.32	1.22	
103.	BC-16		35.66	0.81	2.51	3.10	10.29	6.55	5.60	4.45	70.66	18.71	1.11	
104.	BC-16		15.68	2.24	4.53	5.15	8.03	3.66	2.58	4.95	68.81	19.95	1.14	
105.	BC-16		19.48	2.03	4.12	4.65	12.58	11.55	6.90	7.41	65.81	20.42	1.10	
106.	BC-16		25.64	0.69	2.43	3.44	10.57	7.37	5.82	4.48	71.90	17.81	1.03	
107.	BC-16		24.58	1.24	3.72	5.01	11.60	6.64	3.82	4.71	67.49	19.61	2.53	
108.	BC-16		15.46	1.95	6.03	7.48	11.80	5.01	3.42	4.41	69.03	18.98	2.01	
109.	BC-16		17.2	3.11	5.50	6.19	8.28	2.59	1.86	5.72	67.16	19.32	2.22	
110.	BC-16		16.78	3.76	6.87	6.66	9.68	2.67	0.84	5.42	66.94	19.16	2.43	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
111.	BC-17		28.24	1.44	3.31	4.34	8.90	5.32	4.07	3.84	70.28	19.48	1.19	
112.	BC-17		16.56	2.78	5.33	6.23	7.86	2.51	2.04	4.7	68.51	19.76	1.56	
113.	BC-17		10.82	4.24	6.02	6.63	6.24	1.06	0.48	5.68	65.90	21.24	1.53	
114.	BC-17		24.38	1.48	3.53	4.24	8.72	4.53	3.25	4.18	67.66	21.39	1.12	
115.	BC-17		31.48	1.26	4.41	4.70	9.35	5.03	4.36	4.1	68.49	19.69	1.93	
116.	BC-17		30.52	1.64	3.67	4.34	8.33	4.57	3.35	4.11	68.20	20.64	1.29	
117.	BC-17		33.82	0.85	3.02	3.81	10.14	6.96	5.77	3.96	69.89	19.79	1.15	
118.	BC-17		16.28	2.23	5.06	5.25	7.88	2.88	1.83	5.08	66.48	21.04	1.31	
119.	BC-17		23.62	1.09	3.40	4.05	6.08	4.73	3.10	4.19	67.77	20.79	1.26	
120.	BC-17		16.52	1.97	4.42	5.88	6.82	4.89	3.44	4.1	67.37	21.19	1.18	
121.	BC-17		13.72	2.46	6.03	7.38	11.92	3.63	2.66	4.19	68.85	19.85	1.09	
122.	BC-17		28.38	1.04	3.70	5.16	12.02	7.17	4.65	3.36	71.07	19.10	1.01	
123.	BC-17		24.82	1.85	5.29	7.44	11.85	5.94	3.41	4.08	68.79	19.23	1.64	
124.	BC-17		28.64	1.34	3.84	5.24	11.20	6.03	3.98	4.27	67.87	19.73	1,97	
125.	BC-17		42.42	0.12	1.54	2.34	12.31	9.77	8.47	3.41	70.89	20.01	0.97	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
126.	BC-18		1.6	2.73	5.42	6.07	9.04	3.56	1.63	5.21	66.13	21.43	1.27	
127.	BC-18		7	3.07	5.85	6.37	10.68	2.54	1.50	5.03	65.73	21.79	1.32	
128.	BC-18		25.9	2.07	4.06	5.01	9.53	5.54	4.01	4.22	67.12	20.99	1.38	
129.	BC-18		11.64	2.65	5.74	6.47	8.23	2.93	2.16	5.03	65.79	21.51	1.29	
130.	BC-18		19.56	1.11	3.81	4.74	13.62	8.65	5.80	6.88	65.77	20.12	1.25	
131.	BC-18		16.18	2.15	4.94	5.18	7.89	2.80	1.72	4.84	66.57	21.07	1.23	
132.	BC-18		6.14	3.22	5.73	5.31	6.56	1.57	0.59	5.5	65.64	20.63	1.85	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
133.	BC-19		24.92	1.03	2.84	3.29	8.63	5.38	4.50	3.47	73.41	16.91	1.08	
134.	BC-19		25.02	1.22	3.23	3.84	8.72	4.87	4.26	3.78	70.80	18.66	1.42	
135.	BC-19		26.88	1.42	3.53	3.99	8.29	4.93	3.63	3.93	70.67	18.75	1.41	
136.	BC-19		13.24	2.25	4.88	4.95	7.72	2.57	1.93	5.24	67.84	19.82	1.39	
137.	BC-19		20.6	2.79	4.67	5.13	7.24	3.36	2.44	5.39	66.53	21.16	1.38	
138.	BC-19		38.28	0.85	2.27	3.48	8.76	6.58	4.64	3.47	70.53	19.53	1.05	
139.	BC-19		32.06	1.44	3.19	3.94	9.10	5.27	3.93	3.79	70.29	19.46	1.05	
140.	BC-19		36.2	1.43	2.75	3.24	9.08	6.30	5.34	3.46	71.59	18.41	1.39	
141.	BC-19		18.5	2.21	4.46	4.99	7.59	2.78	2.33	5.16	67.17	20.76	1.34	
142.	BC-19		21.96	1.76	4.06	4.32	7.24	3.50	2.59	4.33	68.54	19.68	1.49	
143.	BC-19		19.46	1.72	3.69	4.01	8.49	4.45	3.16	4.37	67.79	20.22	1.39	
144.	BC-19		12.52	3.79	6.04	5.94	6.63	1.71	0.45	6.73	63.70	22.03	1.50	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
145.	BC-20		27.74	0.77	3.15	3.72	11.07	6.70	5.18	2.64	77.91	14.15	0.89	
146.	BC-20		16.1	1.63	4.00	4.75	9.63	4.74	2.98	4.07	72.58	17.24	1.25	
147.	BC-20		31.86	0.99	2.47	3.04	9.10	6.54	4.82	3.94	70.76	18.77	1.50	
148.	BC-20		12.78	2.27	4.57	4.72	7.87	3.24	2.02	4.49	67.66	20.69	1.35	
149.	BC-20		28.84	2.05	4.29	4.63	7.98	3.58	2.62	4.29	69.44	19.45	1.35	
150.	BC-20		28.78	1.26	3.23	3.80	8.34	5.05	4.10	3.87	70.30	19.23	1.13	
151.	BC-20		21.96	3.73	6.25	6.88	8.86	2.92	3.80	4.77	64.65	22.72	1.79	
152.	BC-20		25.3	1.95	4.49	4.87	9.44	5.98	4.13	4.87	65.77	21.83	1.69	
153.	BC-20		22.56	2.54	4.83	5.43	9.72	4.89	2.83	4.62	66.07	21.57	1.75	
154.	BC-20		20.94	1.63	3.43	4.28	8.77	4.91	3.59	4.25	69.35	19.24	1.49	
155.	BC-20		27.18	2.01	3.95	4.26	7.48	4.56	3.11	3.92	68.56	20.48	1.09	
156.	BC-20		2.74	3.97	6.18	6.25	7.05	1.15	0.30	6.13	64.73	21.12	1.55	
157.	BC-20		25.1	1.91	4.31	4.71	8.38	3.99	2.95	4.17	66.59	21.48	1.43	
158.	BC-20		34.2	1.26	2.97	3.51	8.99	5.60	4.56	3.9	70.72	19.14	1.39	
159.	BC-20		33.26	0.97	2.96	2.38	9.68	5.81	4.42	4.65	67.63	19.06	2.05	
160.	BC-20		31.68	0.95	2.94	3.58	9.29	5.91	4.31	4.14	69.63	19.50	1.24	
161.	BC-20		30.02	1.38	3.82	4.41	9.29	4.43	3.47	4.39	70.12	18.67	1.67	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
162.	BC-21		7.16	6.42	7.58	7.01	3.38	0.22	0.19	6.49	62.81	22.67	1.78	
163.	BC-21		26.16	2.07	4.51	4.86	7.64	3.31	2.42	4.16	70.87	18.58	1.24	
164.	BC-21		24.94	1.52	3.78	4.39	8.11	4.11	2.65	4.3	69.09	19.85	1.19	
165.	BC-21		22.48	2.55	4.46	5.17	7.01	3.52	1.85	4.75	68.19	19.77	1.39	
166.	BC-21		58.52	0.08	1.05	1.56	10.33	8.41	7.61	2.84	72.54	18.44	0.94	
167.	BC-21		24.58	2.22	4.67	6.43	11.59	6.85	5.97	3.96	69.35	19.69	1.35	
168.	BC-21		40.04	1.11	2.46	3.14	8.70	6.15	4.66	3.33	70.44	19.59	1.31	
169.	BC-21		30.6	1.68	3.45	4.36	8.21	4.92	3.22	4.46	68.42	20.38	1.27	
170.	BC-21		28.94	2.44	4.88	6.16	10.31	4.73	3.20	4.48	66.33	21.92	1.30	
171.	BC-21		39.36	0.77	2.25	2.98	10.05	7.63	6.39	4.01	69.62	19.63	1.82	
172.	BC-21		35.44	1.22	3.49	4.32	9.82	5.35	3.88	4.5	70.02	19.01	1.22	
173.	BC-21		40.54	0.69	2.36	2.90	11.46	9.13	3.48	4.78	71.48	17.89	1.25	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
174.	BC-22		20.34	4.84	7.67	7.76	11.18	5.93	3.48	5.28	65.63	20.76	2.52	
175.	BC-22		16.4	4.17	6.16	5.46	9.16	1.09	0.73	5.5	66.89	20.01	1.65	
176.	BC-22		19.12	2.25	4.10	4.65	7.83	4.02	2.62	4.65	68.31	20.16	1.49	
177.	BC-22		15.12	3.86	5.71	6.09	6.59	1.30	0.76	5.64	65.44	21.56	1.53	
178.	BC-22		9.26	4.62	6.70	6.67	6.26	0.29	0.07	5.89	65.27	21.36	1.57	
179.	BC-22		25.14	2.56	4.34	5.68	8.04	3.70	1.54	5.14	66.88	20.73	1.41	
180.	BC-22		20.96	2.76	5.41	5.49	7.83	4.18	1.96	4.87	67.30	20.48	1.62	
181.	BC-22		27.78	2.44	4.77	5.22	8.13	3.71	2.58	4.7	68.21	19.65	1.80	
182.	BC-22		25.62	3.14	5.88	6.43	9.88	5.18	3.21	5.72	64.89	20.40	1.90	
183.	BC-22		37.84	1.75	3.47	4.31	9.43	5.51	4.62	5.42	65.66	19.63	1.97	
184.	BC-22		27.34	1.99	3.99	4.66	9.09	4.85	2.98	5.32	66.02	20.71	1.80	
185.	BC-22		26.24	2.91	4.96	5.21	7.70	3.18	2.32	5.6	65.26	19.95	2.07	
186.	BC-22		18.92	2.15	5.55	6.14	11.68	5.84	4.22	4.68	67.44	20.17	1.69	
187.	BC-22		33.18	2.62	4.35	4.75	11.20	6.40	5.16	4.14	66.40	21.92	1.35	
188.	BC-22		39.56	1.05	2.70	3.43	9.61	6.00	4.99	4.34	69.29	18.21	1.88	
189.	BC-22		51.74	1.71	3.48	4.98	10.77	6.75	6.31	5.24	63.79	20.65	3.50	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
190.	BC-23		37.62	3.04	5.00	5.30	7.25	3.46	2.48	4.49	68.81	18.32	2.55	
191.	BC-23		32.54	1.18	3.05	3.55	8.54	5.10	3.89	3.76	67.36	20.61	2.07	
192.	BC-23		16.24	3.56	5.70	5.67	6.38	1.35	0.44	5.67	65.09	20.13	1.93	
193.	BC-23		19.18	2.88	5.46	5.66	7.21	1.90	1.32	5	66.30	20.55	1.64	
194.	BC-23		25.8	3.65	6.27	5.96	6.56	0.33	0.18	5.8	64.21	21.67	1.89	
195.	BC-23		36.2	1.91	4.13	4.59	8.36	4.07	2.79	4.65	68.06	19.13	1.72	
196.	BC-23		23.28	2.80	4.86	4.98	7.91	3.68	2.77	4.59	66.02	20.32	1,90	
197.	BC-23		28.16	2.03	4.02	4.45	7.92	3.93	3.01	4.58	67.12	20.51	1,76	
198.	BC-23		31.16	1.43	3.08	3.59	8.65	5.78	4.53	3.58	69.63	19.19	1.89	
199.	BC-23		28.42	1.77	2.26	4.01	8.71	5.68	4.24	4.37	68.64	19.47	1.95	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Boja
				1100	1200	1250	1100	1200	1250					
200.	BC-24		17.64	2.25	4.32	4.97	8.03	4.06	2.29	4.72	66.68	21.22	1.26	
201.	BC-24		17.64	2.64	5.23	5.45	7.18	1.94	0.66	5.36	65.49	21.59	1.49	
202.	BC-24		39.24	0.53	1.90	2.63	10.41	7.56	6.00	3.83	70.66	19.11	1.01	
203.	BC-24		16.16	1.09	3.78	4.53	9.43	4.84	3.47	4.01	69.83	19.40	1.13	
204.	BC-24		17.1	1.34	3.81	4.56	9.48	4.68	3.52	5.12	66.61	19.44	2.50	
205.	BC-24		11.36	2.70	4.52	5.44	9.06	3.33	1.02	5.14	65.92	20.78	1.93	
206.	BC-24		24.8	1.54	3.74	4.22	8.12	4.49	3.66	5.26	67.49	19.38	2.05	
207.	BC-24		21.94	1.87	4.20	4.20	8.37	4.13	3.67	5.2	66.50	19.69	1.87	
208.	BC-24		37	0.59	2.11	2.81	9.19	6.23	5.63	4.05	71.64	17.90	1.22	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
209.	BC-25		32.84	0.18	1.66	2.13	9.82	7.37	5.35	2.4	76.28	15.72	0.96	
210.	BC-25		23.04	1.48	3.39	3.95	8.91	5.10	4.02	3.85	71.05	18.14	1.41	
211.	BC-25		20.36	1.81	3.75	4.28	7.53	3.52	2.02	4.41	69.23	19.34	1.37	
212.	BC-25		18.68	1.72	4.09	4.68	7.97	3.43	2.46	4.55	67.84	19.63	1.62	
213.	BC-25		23.24	2.60	4.61	5.06	7.96	4.05	2.48	4.89	67.33	19.85	2.38	
214.	BC-25		2.22	2.97	5.85	6.22	7.33	2.36	0.29	5.7	64.25	21.53	1.73	
215.	BC-25		22.06	1.36	3.32	4.09	8.93	5.08	3.53	4.19	68.83	19.10	1.55	
216.	BC-25		18.34	2.66	4.88	5.33	7.44	3.64	2.15	4.41	68.99	18.73	1.80	
217.	BC-25		24.04	1.42	3.96	4.30	8.79	4.62	3.51	5.63	65.74	19.07	3,07	
218.	BC-25		24.74	1.70	3.81	4.27	8.49	4.73	3.21	4.9	67.64	19.67	1.78	
219.	BC-25		17.16	2.47	4.84	4.73	6.23	1.36	0.48	5.38	63.68	22.20	1.69	
220.	BC-25		19.54	1.94	4.19	4.64	8.48	4.39	3.45	5.74	65.33	21.10	1.40	
221.	BC-25		44.76	0.28	1.60	1.95	10.01	7.53	6.83	3.12	71.58	18.17	1.27	
222.	BC-25		6.38	3.29	6.09	6.01	6.72	1.07	0.37	5.9	64.72	20.79	1.80	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
223.	BC-26		34.02	0.77	2.27	2.86	9.66	6.78	5.72	3.53	72.71	17.77	1.11	
224.	BC-26		26.56	1.97	3.93	4.36	7.91	3.77	2.89	4.45	68.94	19.74	1.31	
225.	BC-26		7.48	5.29	9.39	9.12	8.17	1.49	0.36	6.3	64.08	22.21	1.56	
226.	BC-26		0.96	6.27	9.94	9.41	6.02	0.11	0.04	7.01	62.15	23.13	1.74	
227.	BC-26		13.48	2.96	5.89	6.80	11.82	4.72	2.67	4.91	67.73	20.26	1.40	
228.	BC-26		24.32	2.97	4.71	5.55	8.68	4.23	2.84	4.89	67.84	19.49	1,81	
229.	BC-26		26.4	3.32	5.33	5.98	11.11	5.61	4.11	4.23	68.36	19.80	1.72	
230	BC-26		34.14	1.65	3.17	3.78	10.14	6.53	5.04	4.82	67.44	18.60	3.72	
231	BC-26		30.22	2.63	4.30	5.05	9.49	5.90	4.34	5.52	65.73	19.04	4.16	
232	BC-26		36.04	1.44	2.88	4.00	9.86	5.49	4.67	4.63	68.97	18.90	2.24	

Broj uzor ka	Oznaka uzorka	Metraža	Ostatak na situ (%)	Skup. u peč. (%)			UV (%)			GŽ	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	
				1100	1200	1250	1100	1200	1250					
233.	BC-27		9.44	4.74	6.01	5.47	4.84	0.62	0.37	5.87	65.27	21.50	1.47	
234.	BC-27		13.98	3.67	5.34	5.41	6.11	2.88	1.39	5.5	66.27	20.83	1.45	
235.	BC-27		6.88	4.22	6.01	5.84	5.23	0.67	0.33	6.02	64.65	21.78	1.57	
236.	BC-27		16.2	2.25	4.36	4.73	8.12	2.51	2.99	5.02	68.17	19.94	1.46	
237.	BC-27		31.2	1.42	3.40	4.17	9.19	5.39	3.94	3.95	68.76	19.68	1.81	
238.	BC-27		28.98	1.30	3.22	3.59	6.81	5.27	4.06	4.47	68.85	20.04	1.39	
239.	BC-27		23.82	1.46	3.69	4.12	9.62	5.42	3.90	5.51	68.06	19.38	1.18	
240.	BC-27		16.82	2.05	4.26	4.54	8.41	4.26	2.82	4.93	67.14	20.72	1.18	
241.	BC-27		27.02	2.33	4.16	4.62	8.79	4.92	3.10	6.31	65.39	21.44	1.09	
242.	BC-27		11.3	3.11	5.86	6.18	7.63	2.22	1.00	6.83	61.52	23.37	1.82	
243.	BC-27		23.32	1.95	4.88	5.55	9.68	4.59	3.18	5.31	66.98	19.87	1.71	
244.	BC-27		26.84	1.08	3.33	4.50	10.52	6.78	4.32	4.01	71.91	17.25	1.45	
245.	BC-27		30.66	0.63	2.87	3.55	10.81	7.61	6.01	3.32	72.43	17.37	1.46	
246.	BC-27		36.88	0.55	2.42	3.73	11.58	8.44	5.97	3.77	73.67	15.90	2.16	
247.	BC-27		12.08	3.90	3.91	/	6.70	0.26	/	5.61	61.90	20.00	4.50	
248.	BC-27		2.94	4.98	2.74	/	5.40	0.62	/	4.89	62.33	18.87	5.42	
249.	BC-27		22.84	5.57	1.65	/	5.27	0.62	/	5.43	59.16	19.78	6.29	
250.	BC-27		20.8	5.99	0.47	/	4.58	2.49	/	5.63	59.93	19.69	5.79	